



Cosmetics

RR 8019

Baycusan® C 1004 Liquid Eyeliner

		% by wt.
Phase A	Water	64.70
	Xanthan Gum ¹⁾	0.80
Phase B	Black Iron Oxide	10.00
Phase C	Laureth-4	1.00
	Propylene Glycol	2.00
	Phenoxyethanol (and) Ethylhexylglycerin	1.00
	PEG-10 Dimethicone	0.50
	Baycusan® C 1004	20.00
		100.00
Raw materials	1) Keltrol® CG-T, CP Kelco	
Processing	Disperse Xanthan Gum into water. When the phase A is uniform, add phase B and homogenize until uniform. While stirring, add phase C.	

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.

Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Published by: Coatings, Adhesives & Specialties
Covestro AG
51373 Leverkusen, Germany
www.cosmetics.covestro.com

Contact: Sophie Viala
Phone: +49 214 6009 4476